

**GMA-400G  
ACRYLIC RESIN  
FOR POWDER COATINGS**

[www.estron.com](http://www.estron.com)



THE EDGE OF INNOVATION

**GENERAL DESCRIPTION**

GMA-400G is solid, high-functionality glycidyl acrylic polymers of identical composition but differing particle sizes capable of reacting with carboxyl and amine functional compounds. They can be used either as sole curing agents for acid-functional polyester resins to make polyester/acrylic hybrids, or as fortifying additive resins at low loadings in systems such as polyester/TGIC or hybrid systems to boost crosslink density and increase film hardness/chemical resistance.

As with any raw material, laboratory evaluation is recommended for each formulation to determine the best processing method and the optimum concentration of GMA-400G.

**TYPICAL PROPERTIES\***

Appearance	Clear Ground Flake
Gardner color	< 1
Non-Volatile, weight %	99.5% minimum
Epoxy Equivalent Weight (g/equivalent)	390 – 420

\* Not to be used for specification purposes

**REGULATORY LISTINGS**

The components of this material are either listed or exempt from listing due to polymer exemption criteria for the following chemical inventory listings: AICS (Australia), DSL (Canada), ECN (Taiwan), EINECS (Europe), ENCS (Japan), IECSC (China), KECI (Korea), NZIoC (New Zealand), PICCS (Philippines), TSCA (USA)

**PACKAGING (NET WEIGHT)**

55 lb. / 25 kg in fiberboard box with polyolefin liner

**PRODUCT AVAILABILITY**

GMA-400G is available in commercial quantities. Please contact your Estron Sales Representative for samples, lead time and availability.

**STORAGE AND HANDLING**

Keep container tightly closed and store in a dry, well ventilated area away from heat and sources of ignition. Store at less than 100°F (38°C). Shelf life of unopened containers is one year from date of shipment. See SDS for additional information.

**CONTACT INFORMATION**

807 N. Main Street

P.O. Box 127

Calvert City, KY 42029 USA

(270) 395-4195 PHONE

(270) 395-5070 FAX

Revision Date: February 2, 2017

TDS Revised by: A. Chizhikova

TDS Approved by: F. Allen