

**RESIFLOW® 3N
FLOW CONTROL AGENT
FOR WATERBORNE COATINGS**

www.estron.com



THE EDGE OF INNOVATION

GENERAL DESCRIPTION

Resiflow® 3N is a leveling agent for use in waterbased coatings. It is beneficial in alleviating brush and roller marks, picture framing, edge pull and sagging, as well as promoting a uniform, level surface. Resiflow® 3N is supplied as a 75% polymer solution in Glycol Ether EB (ethylene glycol monobutyl ether) and is made water soluble by neutralization with ammonia or a tertiary amine. Neutralize each 100 grams of Resiflow® 3N with 0.085 equivalents of base.

In its supplied form, Resiflow® 3N can also be incorporated into high solids and solvent based coatings.

TYPICAL PROPERTIES*

Appearance	Clear Liquid
Gardner Color	1 maximum
Specific Gravity (25/25)	1.04 – 1.08
Gardner Viscosity	Y – Z ₂
Non-Volatile, weight %	73 – 77%
Acid value, mg KOH / gram	50 – 60

* Not to be used for specification purposes

REGULATORY LISTINGS

The components in this material are either listed or exempt from listing due to polymer exemption criteria for the following chemical listing inventories: AICS (Australia), DSL (Canada), ECL (Korea), EINECS (Europe), ENCS (Japan), IECSC (China), NZIoC (New Zealand), PICCS (Philippines), TSCA (USA).

Resiflow® 3N is compliant with 21 CFR 175.300. The finished coating must meet the extractive requirements of 21 CFR 175.300. This aspect of compliance is the responsibility of the manufacturer or user of the finished coating.

PACKAGING (NET WEIGHT)

40 lb. / 18.1 kg in steel pail

440 lb. / 199.6 kg in steel drum

PRODUCT AVAILABILITY

This product is commercially available and may require lead time.

STORAGE AND HANDLING

Keep container tightly closed and store in a dry, well ventilated area away from extreme heat, open flame or sources of ignition. Shelf life of unopened containers is 1 year from date of shipment. See SDS for additional information.

CONTACT INFORMATION

807 N. Main Street

P.O. Box 127

Calvert City, KY 42029 USA

(270) 395-4195 PHONE

(270) 395-5070 FAX

Revision Date: October 9, 2017 TDS Revised by: A. Chizhikova TDS Approved by: F. Allen