

**RESIFLOW® L-210
FLOW CONTROL AGENT
FOR THE COATINGS INDUSTRY**



THE EDGE OF INNOVATION

www.estron.com

GENERAL DESCRIPTION

Resiflow® L-210 is a low viscosity, non-reactive acrylic polymer used as a leveling agent in high solids, UV curing, coil, and other coating systems. Resiflow® L-210 can also facilitate air release and minimize surface imperfections such as pinholes and craters. It has excellent compatibility with all coating systems including acrylic, alkyd, phenolic, epoxy, polyester, polyurethane, nitrocellulose lacquer, and other systems.

The recommended level of usage is between 0.2-1.5% calculated on the coating binder. The method of incorporating Resiflow® L-210 into coating formulations does not affect the performance of the coating as long as it is uniformly dispersed in the system. This can be easily achieved by thoroughly mixing Resiflow® L-210 with the other paint ingredients. As with any raw material, laboratory evaluation is required for each formulation to determine the best processing method and the optimum concentration of the additive.

TYPICAL PROPERTIES*

Appearance	Clear Liquid
Gardner Color	2 maximum
Specific Gravity (25/25)	1.01 – 1.03
Gardner Viscosity, 80% SOLIDS IN XYLENE	Q - U
Non-Volatile, weight %	98.5% minimum
Acid value (mg KOH/gram)	1 maximum

* Not to be used for specification purposes

REGULATORY LISTINGS

The components in this material are either listed or exempt from listing due to polymer exemption criteria for the following chemical listing inventories: AICS (Australia), DSL (Canada), ECL (Korea), ECN (Taiwan), EINECS (Europe), ENCS (Japan), IECSC (China), NZIoC (New Zealand), PICCS (Philippines), TSCA (USA).

Resiflow® L-210 is compliant with 21 CFR 175.300. The finished coating must meet the extractive requirements of 21 CFR 175.300. This aspect of compliance is the responsibility of the manufacturer or user of the finished coating.

PACKAGING (NET WEIGHT)

44 lb. / 20.0 kg in steel pail

440 lb. / 199.6 kg in steel drum

PRODUCT AVAILABILITY

This product is commercially available and may require lead time. Contact your Estron Sales Representative.

STORAGE AND HANDLING

Keep container tightly closed and store in a dry, well ventilated area away from heat and sources of ignition. Shelf life of unopened containers is 1 year from date of shipment. See SDS for additional information.

CONTACT INFORMATION

807 N. Main Street

P.O. Box 127

Calvert City, KY 42029 USA

(270) 395-4195 PHONE

(270) 395-5070 FAX

Revision Date: July 8, 2016

TDS Revised by: A. Buckhalter

TDS Approved by: F. Allen

Page 1 of 1

This information is not to be taken as warranty or representation for which we assume legal responsibility nor as permission or recommendation to practice any patented invention without a license. It is offered solely for your consideration, investigation, and verification. Neither seller nor manufacturer shall be liable for any injury, loss or damage arising out of the use of the product.