

**RESIFLOW® L-37
FLOW CONTROL AGENT
FOR THE COATINGS INDUSTRY**



THE EDGE OF INNOVATION

www.estron.com

GENERAL DESCRIPTION

Resiflow® L-37 is a silicone-free, 100% solids, reactive polyacrylate additive for high solids, solvent-based, free radical UV, cationic, coil, and general industrial coatings, inks and adhesives.

Resiflow® L-37 has been tested in various formulations and is especially effective in urethane acrylates, epoxy acrylates, polyesters, and epoxies. Recommended level of usage is 0.1%-0.5% based on solids. It can be cut in various reactive diluents, aromatic and aliphatic hydrocarbons, esters, ketones, or alcohols for easy incorporation into the formula. As with any raw material, laboratory evaluation is required for each formulation to determine the best processing method and the optimum concentration of the additive.

KEY ATTRIBUTE SUMMARY:

- Enhanced resistance against air entrapment; promotes air release
- Improved mar and stain resistance
- Reduced pigment floating
- Reduced formation of Benard cell structures and fish-eyes
- Increased gloss

TYPICAL PROPERTIES*

Appearance	Clear Liquid
Gardner Color	3 max
Specific Gravity (25/25)	1.01 – 1.03
Gardner Viscosity, 80% SOLIDS IN XYLENE	U – Y
Non-Volatile, weight %	97.0% minimum
Acid value, mg KOH / gram	5 max

* Not to be used for specification purposes

REPRESENTATIVE FORMULATION

Resiflow L-37 was compared to a number of silicone and other defoamers for anti-foam and air release characteristics in the following formulation.

Cyacure UVR 6105 (Dow)	81.5 parts
Tone 0301 (Dow)	4.0 parts
Heloxy 505 (Hexion)	5.0 parts
Limonene Dioxide (Lyondell)	5.0 parts
UVI 6990 (Dow)	4.0 parts
Resiflow L-37 (Estron Chemical, Inc.)	0.5 parts

The formulation was tested by going through 2 cycles (5 minutes each) in a paint can shaker.

VISUAL OBSERVATIONS:

- Resiflow L-37 significantly lowered foam and air entrapment in comparison to silicone additives.
- Resiflow L-37 induced much faster disappearance of air bubbles/foam in comparison to other additives.
- Resiflow L-37 does not interfere with wetting characteristics and forms a clear solution on various substrates including, vinyl, aluminized paper, Corona treated oriented polypropylene, and polyethylene at 0.5 mil film thickness.

**RESIFLOW® L-37
FLOW CONTROL AGENT
FOR THE COATINGS INDUSTRY**

www.estron.com



THE EDGE OF INNOVATION

- Similar observations were made when Resiflow L-37 was tested in urethane acrylates, epoxy acrylates, free radical clear and pigmented formulations. Resiflow L-37 stabilized coating formulations against entrapment of air and reduced tendency to foam, especially in high-speed environments.

REGULATORY LISTINGS

The components in this material are either listed or exempt from listing due to polymer exemption criteria for the following chemical listing inventories: DSL (Canada), EINECS (Europe), TSCA (USA)

PACKAGING (NET WEIGHT)

44 lb. / 20 kg in steel pail

440 lb. / 199.6 kg in steel drum

PRODUCT AVAILABILITY

This product is commercially available and may require lead time.

STORAGE AND HANDLING

Store in a dry, cool area and avoid excessive heat. Shelf life of unopened containers is one year from date of shipment. Refer to the SDS for additional information.

CONTACT INFORMATION

807 N. Main Street

P.O. Box 127

Calvert City, KY 42029 USA

(270) 395-4195 PHONE

(270) 395-5070 FAX

Revision Date: September 12, 2017

TDS Revised by: A. Chizhikova

TDS Approved by: F. Allen