

**RESIFLOW® L-64F  
FLOW CONTROL AGENT  
FOR THE COATINGS INDUSTRY**

[www.estron.com](http://www.estron.com)



THE EDGE OF INNOVATION

**GENERAL DESCRIPTION**

Resiflow® L-64F is a carboxyl functional, viscous acrylic flow control agent that can be used in high solids, solvent borne, UV curable, and other paint systems. Resiflow® L-64F can act as an air release agent, reduce or eliminate surface defects such as craters, pinholes and fisheyes as well as improve flow and leveling.

The recommended dosage of Resiflow® L-64F is 0.2-1.5% based on binder solids. As with any raw material, laboratory evaluation is required for each formulation to determine the best processing method and the optimum concentration of the additive.

Resiflow® L-64F is also available in several resin masterbatches for powder coatings, as well as in the powder form Resiflow® P-64F for clear GMA Acrylic-DDDA powder coating systems.

**TYPICAL PROPERTIES\***

Appearance	Clear Liquid
Gardner Color	1 max
Specific Gravity	1.01 - 1.03
Non-Volatile, weight %	98.5% minimum

\* Not to be used for specification purposes

**REGULATORY LISTINGS**

The components in this material are either listed or exempt from listing due to polymer exemption criteria for the following chemical listing inventories: AICS (Australia), DSL (Canada), ECL (Korea), EINECS (Europe), ENCS (Japan), IECSC (China), NZIoC (New Zealand), TSCA (USA)

**PACKAGING (NET WEIGHT)**

44 lb. / 20.0 kg in steel pail

440 lb. / 199.6 kg in steel drum

**PRODUCT AVAILABILITY**

This product is commercially available and may require lead time.

**STORAGE AND HANDLING**

Keep container tightly closed and store in a dry, well ventilated area away from heat and sources of ignition. Store at less than 100°F (38°C). Shelf life of unopened containers is 1 year from date of shipment. See SDS for additional information.

**CONTACT INFORMATION**

807 N. Main Street

P.O. Box 127

Calvert City, KY 42029 USA

(270) 395-4195 PHONE

(270) 395-5070 FAX

Revision Date: June 4, 2014

TDS Revised by: G. Pearson

TDS Approved by: R. Auerbach