

**RESIFLOW® L-64F
FLOW CONTROL AGENT
FOR THE COATINGS INDUSTRY**

www.estrone.com



THE EDGE OF INNOVATION

GENERAL DESCRIPTION

Resiflow® L-64F is a carboxyl functional, viscous acrylic flow control agent that can be used in high solids, solvent borne, UV curable, and other paint systems. Resiflow® L-64F can act as an air release agent, reduce or eliminate surface defects such as craters, pinholes and fisheyes as well as improve flow and leveling.

The recommended dosage of Resiflow® L-64F is 0.2-1.5% based on binder solids. As with any raw material, laboratory evaluation is required for each formulation to determine the best processing method and the optimum concentration of the additive.

Resiflow® L-64F is also available in several resin masterbatches for powder coatings, as well as in the powder form Resiflow® P-64F for clear GMA Acrylic-DDDA powder coating systems.

TYPICAL PROPERTIES*

| | |
|------------------------|---------------|
| Appearance | Clear Liquid |
| Gardner Color | 1 max |
| Specific Gravity | 1.01 - 1.03 |
| Non-Volatile, weight % | 98.5% minimum |

* Not to be used for specification purposes

REGULATORY LISTINGS

The components in this material are either listed or exempt from listing due to polymer exemption criteria for the following chemical listing inventories: AICS (Australia), DSL (Canada), ECL (Korea), EINECS (Europe), ENCS (Japan), IECSC (China), NZIoC (New Zealand), TSCA (USA)

PACKAGING (NET WEIGHT)

44 lb. / 20.0 kg in steel pail

440 lb. / 199.6 kg in steel drum

PRODUCT AVAILABILITY

This product is commercially available and may require lead time.

STORAGE AND HANDLING

Store in a dry, cool area and avoid excessive heat. Shelf life of unopened containers is one year from date of shipment. Refer to the SDS for additional information.

CONTACT INFORMATION

807 N. Main Street

P.O. Box 127

Calvert City, KY 42029 USA

(270) 395-4195 PHONE

(270) 395-5070 FAX

Revision Date: September 12, 2017

TDS Revised by: A. Chizhikova

TDS Approved by: F. Allen