

**RESIFLOW® L-66F
FLOW CONTROL AGENT
FOR THE COATINGS INDUSTRY**



THE EDGE OF INNOVATION

www.estron.com

GENERAL DESCRIPTION

Resiflow L-66F is a high viscosity, carboxyl functional polyacrylate flow control agent. It can be used in a variety of coating systems and provides exceptional clarity in clearcoat systems. As with the other two carboxyl functional flow control agents in this group of specialty additives, Resiflow L-64F and L-65F, the typical dosage of Resiflow L-66F is 0.2 – 1.5% based on binder solids. Laboratory evaluation is required for each formulation to determine the best processing method and the optimum concentration of the additive.

For powder coating clearcoat applications, Resiflow L-66F is available in several resin masterbatches.

TYPICAL PROPERTIES*

Appearance	Clear liquid
Gardner Color	1 max
Non-Volatile, weight %	98.0% minimum

* Not to be used for specification purposes

REGULATORY LISTINGS

The components in this material are either listed or exempt from listing due to polymer exemption criteria for the following chemical listing inventories: AICS (Australia), DSL (Canada), ECL (Korea), ECN (Taiwan), EINECS (Europe), ENCS (Japan), IECSC (China), NZIoC (New Zealand), TSCA (USA)

PACKAGING (NET WEIGHT)

44 lb. / 20.0 kg in steel pail

440 lb. / 199.6 kg in steel drum

PRODUCT AVAILABILITY

This product is made to order and requires lead time.

STORAGE AND HANDLING

Store in a dry, cool area and avoid excessive heat. Shelf life of unopened containers is 1 year from date of shipment. See SDS for additional information.

CONTACT INFORMATION

807 N. Main Street

P.O. Box 127

Calvert City, KY 42029 USA

(270) 395-4195 PHONE

(270) 395-5070 FAX

Revision Date: June 10, 2014

TDS Revised by: G. Pearson

TDS Approved by: R. Auerbach