

RESIFLOW® L-66F MBP-10 FLOW CONTROL MASTERBATCH FOR POWDER COATINGS

www.estron.com



THE EDGE OF INNOVATION

GENERAL DESCRIPTION

Resiflow® L-66F MBP-10 is a 10% flow control masterbatch of Resiflow L-66F in Cytec's Crylcoat 2437-0 carboxyl polyester resin for TGIC. This masterbatch has been designed for good flow and optimal clarity in PE-TGIC clearcoat formulations. A key attribute of this flow control masterbatch is that the Resiflow L-66F has already been highly dispersed into the polyester resin and thus is very easily incorporated into the final formulation.

Typical dosage is 7-12% based on the total formulation. The formulator will need to reduce the base polyester resin in the formulation to accurately compensate for the polyester resin contained in the masterbatch. This will maintain the correct resin to crosslinker ratio.

For each new formulation, an individual laboratory test is required to determine the optimum concentration of the additive and processing conditions.

TYPICAL PROPERTIES*

| | |
|------------------------------|---------------------------|
| Appearance | White to Off White Flakes |
| Activity, weight % | 9 – 11% |
| Softening Point, RING & BALL | 103 - 113°C |

* Not to be used for specification purposes

REGULATORY LISTINGS

The components in this material are either listed or exempt from listing due to polymer exemption criteria for the following chemical listing inventories: DSL*(Canada), ECL (Korea), EINECS (Europe), ENCS (Japan), IECSC (China), NDSL* (Canada), TSCA (USA)

* The Resiflow L-66F is listed on the DSL; the Crylcoat 2437-0 is listed on the NDSL.

PACKAGING (NET WEIGHT)

200 lb. / 90.7 kg in fiber drum with polyolefin liner

44 lb. / 20.0 kg in fiberboard box with polyolefin liner

PRODUCT AVAILABILITY

This product is commercially available and may require lead time.

STORAGE AND HANDLING

Store in a dry, cool area and avoid excessive heat. Keep containers tightly closed. Store at less than 100°F (38°C). Shelf life of unopened containers is two years from date of manufacture. Refer to the SDS for additional information.

CONTACT INFORMATION

807 N. Main Street

P.O. Box 127

Calvert City, KY 42029 USA

(270) 395-4195 PHONE

(270) 395-5070 FAX

Revision Date: September 22, 2017

TDS Revised by: A. Chizhikova

TDS Approved by: F. Allen