

**RESIFLOW® L-68
FLOW CONTROL AGENT
FOR THE COATINGS INDUSTRY**

www.estron.com



THE EDGE OF INNOVATION

GENERAL DESCRIPTION

Resiflow® L-68 is an acrylic polymer solution in Solvent 150. When added in prescribed concentrations, Resiflow® L-68 will correct surface imperfections and minimize air entrapment. Resiflow® L-68 exhibits excellent hydrolytic stability and outdoor durability.

The recommended level of usage is between 0.4 - 3.0%, calculated on the coating binder content. The method of incorporating Resiflow® L-68 into formulations does not affect the performance of the coating provided that it is uniformly dispersed in the systems. This can be easily achieved by thoroughly mixing Resiflow® L-68 with the other paint ingredients.

TYPICAL PROPERTIES*

| | |
|---------------------------|-------------------------------|
| Appearance | Clear to Slightly Haze Liquid |
| Gardner Color | 2 max. |
| Specific Gravity (25/25) | 0.96 |
| Gardner Viscosity | <A |
| Non-Volatile, weight % | 60% |
| Acid value, mg KOH / gram | 2 max. |

* Not to be used for specification purposes

APPLICATIONS

Resiflow® L-68 is used to improve flow and minimize air entrapment, orange-peel, pinholes, craters, and other surface defects in coatings and lacquers. It can be used in acrylics, alkyds, phenolics, epoxies, epoxy-phenolics, polyesters, polyurethanes, nitrocellulose lacquers, and other systems.

REGULATORY LISTINGS

The components in this material are either listed or exempt from listing due to polymer exemption criteria for the following chemical listing inventories: AICS (Australia), EINECS (Europe), NZIoC (New Zealand), TSCA (USA).

PACKAGING (NET WEIGHT)

440 lb. / 199.6 kg in steel drum

PRODUCT AVAILABILITY

This product is commercially available.

STORAGE AND HANDLING

Keep container tightly closed and store in a dry, well ventilated area away from extreme heat, open flame or sources of ignition. Store locked up. Shelf life of unopened containers is 1 year from date of shipment. See SDS for additional information.

CONTACT INFORMATION

807 N. Main Street
P.O. Box 127
Calvert City, KY 42029 USA

(270) 395-4195 PHONE
(270) 395-5070 FAX

Revision Date: October 9, 2017 TDS Revised by: A. Chizhikova TDS Approved by: F. Allen